

TECHNICAL DATA SHEET

----- PAINT DIVISION -----

SteryPaint

sez. 1.0 Technical characteristic

STERYLPAIN is a special, vapour permeable, anti mould, washable paint that is particularly effective in the prevention of the development of mould and algae, especially in environments where there is a high level of humidity (kitchens, bathrooms, swimming pools etc.). The special bactericides and fungicides used in its formulation act on a wide range of micro organisms and protect the wall for a long time. It has a low level of odour, is non flammable and is friendly to both humans and the environment.

sez. 2.0 Ideal Use

Interior walls with problems of mould and algae.

sez. 3.0 Surface preparation

Prepare the affected surface by removing moulds/algae by using Steryfix by OIKOS and the sanitising SterySan by OIKOS.

sez. 4.0 Application method

Using a roller or brush, apply a first coat of STERYLPAIN diluted 30÷40% with drinkable water. After approximately 6÷8 hours proceed with the application of a second coat of the product diluted 25÷30% with drinkable water. STERYLPAIN can be applied as a preventive measure also on healthy walls, in which case the application of preparatory products is not necessary.

sez. 6.0 Technical Characteristic: application

| | |
|--------------------------|--|
| Dilution | First coat: 30 ÷40% with drinkable water. Second coat: 25-30% with drinkable water. |
| Yield | New wall, civil plaster: 7-8 m ² /l in two coats. New wall, gypsum plaster: 9-11 m ² /l in two coats. |
| Tools | Brush, roller |
| Application temperature | +5°C ÷ +36°C (with relative humidity not exceeding 80%) |
| Drying time: tack free | 1 ÷ 1.3 hours (temperature =20°C with relative humidity less than 75%) |
| Drying time: fully cured | 4 days (temperature = 20°C with relative humidity less than 75%) |
| Tools cleaning | Water |

sez. 7.0 Technical Characteristic: the product

| | |
|---|---|
| Composition | Acrylic resins in water dispersion, organic and inorganic pigments, additives aimed at helping application and film formation, anti-mould and anti-algae additives. |
| Specific weight | 1.55 Kg/l ±3% (white) |
| Ph | 8-9.5 |
| Viscosity | 21,000 +/-5% CPS Brookfield (RVT 20 revs/min. a 25°C) |
| Storage temperature | +2°C ÷ +36°C. Keep from freezing |
| Fire reaction | Negative when the product is applied onto a non inflammable surface: water based material with dry thickness of less than 0,600 mm |
| Water vapour permeability (Sd) | 0.37 m (max allowed limit 2 m DIN 52 615) |
| Emission limits of Volatile Organic Compounds (VOC) according to directive 2004/42/CE | Classification: A/a; VOC: 7g/l (max); Limit Phase I (from 01/01/2007): 75g/l, Limit Phase II (from 01/01/ 2010): 30g/l |
| Available colours | White + Pastel Colour Chart from DCS Decor Color System by OIKOS. |
| Packaging | 4 - 14 l |

sez 8.0 Toxicological data

The product is free of heavy metals such as lead or chrome. It does not contain toxic solvents, aromatics or chlorides. There is no risk of any dangerous polymerisation. The product is considered to be a non dangerous substance if used in the technically correct manner. Normal cautionary measures for the handling of water based paints are advised. No special arrangements are required for the storage, movement and transportation of the product; the containers, residue, eventual spilt material should be cleaned up using absorbent inert material such as sand, soil etc. etc. and then disposed of in accordance with the regional and national regulations in force at that time. Transportation must be carried out in accordance with international agreements.

sez. 9.0 Specifications

Clean the surface to be treated and remove loose or flaking materials. Remove moulds/algae by using a detergent such as Sterylfix by OIKOS and a sanitising product such as Sterylsan by OIKOS. Apply two coats of a sterilizing, vapour permeable paint against moulds and algae like STERYLPAINT by OIKOS. All must be carried out in accordance with the norms of application, at a cost of m² inclusive of materials and labour

Note

The company Oikos S.r.l guarantees, to the best of its own technical and scientific knowledge, that the information contained in this technical data sheet is correct. Notwithstanding that indicated above, Oikos takes no responsibility for the results obtained through the use of this product in as much as it is not possible for Oikos to check or control the application method used. For this reason, we recommend that you check carefully that each product chosen, is suitable for each individual use to which it is put.