

TECHNICAL DATA SHEET **ECOFONDO RIEMPITIVO**

Technical Qualities

Coloured, acrylic, ecological undercoat for wood, ideal for use as a base for final coats of enamel. The product is easy to sand and makes the absorption of the wood even covering any imperfections on the surface.

Ideal Use

Base coat for ECOSMALTO by OIKOS

Surface Preparation

Clean the surface to be treated, removing any dirt and dust. Resinous wood must be cleaned with the appropriate products. Use filler if necessary and sand down.

Application Method

Apply one coat of ECOFONDO RIEMPITIVO diluted 5 ÷ 10% drinkable water by brush or roller. After 6 hours sand down using fine sand paper.

Finish

ECOSMALTO UNIVERSALE, ECOSMALTO FERROMICACEO, NOVALIS ECOSMALTO METALLIZZATO by OIKOS.

Technical Characteristics: Application

Dilution	5 ÷ 10% drinkable water
Yield	5 ÷ 6 m ² /l per coat according to the surface
Application tools	Brush for acrylic enamels, roller, spray gun (1,3 ÷ 1,7 mm nozzle)
Application temperature	+5°C ÷ +36°C (relative humidity not higher than 80%)
Drying time: tack free	1÷2 h (temperature= 20°C humidity not higher than 75%)
Drying time: for painting over	6 h (temperature= 20°C humidity not higher than 75%)
Tools cleaning	Water



Technical Characteristics: Product

Composition	acrylic resins in water dispersion, inorganic pigments, mineral fillers, preservatives and additives to aid in application and the formation of the surface film.
Specific weight	1.45kg/l +/-3%
PH	8.5 ÷ 9.5
Viscosity	6.000÷14.000 +/-5% CPS Brookfield (RVT 20 revs/min at 25°C)
Storage temperature	+2°C ÷ +36°C. Keep from freezing
Fire reaction:	negative when the product is applied onto a non inflammable surface: water based material with dry thickness of less than 0.600 mm
Emission limits of Volatile Organic Compounds (VOC) according to directive 2004/42/CE	Classification: A/d; VOC: 25g/l (max); Limit Phase II (from 01/01/ 2010): 130g/l
Colours	White + shades of the colour chart
Packaging	Ltr 0,75 – 2.25

Safety information

The product is free of heavy metals such as lead or chrome. It does not contain toxic solvents, aromatics or chlorides. There is no risk of any dangerous polymerisation. The product is considered to be a non dangerous substance if used in the technically correct manner. Normal cautionary measures for the handling of water based paints are advised. No special arrangements are required for the storage, movement and transportation of the product; the containers, residue, eventual spilt material should be cleaned up using absorbent inert material such as sand, soil etc. etc. and then disposed of in accordance with the regional and national regulations in force at that time. Transportation must be carried out in accordance with international agreements.

Specifications

Clean, degrease and sand down the surface to be treated, removing any loose material. Sand down and if necessary use stucco then apply one coat of an acrylic base such as ECOFONDO RIEMPITIVO by OIKOS and after 6 hours, sand down with a fine sand paper. All must be carried out in accordance with the norms of application, at a cost ofmq. inclusive of materials and labour.

Note

The company Oikos Spa guarantees, to the best of its own technical and scientific knowledge, that the information contained in this technical data sheet is correct. Notwithstanding that indicated above, Oikos takes no responsibility for the results obtained through the use of this product in as much as it is not possible for Oikos to check or control the application method used. For this reason, we recommend that you check carefully that each product chosen, is suitable for each individual use to which it is put.

